

Technical Data Sheet: Ref: TDS-HPC-0001-V02

Date of issue: June 2017

[www.kansaipaint.ir](http://www.kansaipaint.ir)

## A212-2001

### CHLORINATED RUBBER ANTI CORROSIVE INTERMEDIATE

<b>GENERIC TYPE</b>	Chlorinated Rubber																								
<b>DESCRIPTION</b>	A212-2001 is a physically drying, modified chlorinated rubber based intermediate, containing anti corrosive pigment.																								
<b>RECOMMENDED USE</b>	As a water resistant intermediate in underwater and above water systems such as ship hulls, decks & super structures offshore structures, structural steel and piping in chemical plants, refineries, bridges and cranes. It is also suitable for drinking water systems.																								
<b>FEATURE</b>	<ul style="list-style-type: none"> <li>-Excellent water resistance</li> <li>-Durability in severe marine atmosphere</li> <li>-Good penetration</li> <li>-Easy repair</li> </ul>																								
<b>PHYSICAL PROPERTIES</b>	<table border="0"> <tr> <td>Finish</td> <td>Semi flat – Semi gloss</td> </tr> <tr> <td>Color</td> <td>Upon request</td> </tr> <tr> <td>Solid by volume</td> <td>55±5%</td> </tr> <tr> <td>Specific Gravity</td> <td>1.35±0.1 gr/cm<sup>3</sup></td> </tr> <tr> <td>Flash point</td> <td>30 °c</td> </tr> <tr> <td>Recommended D.F.T.</td> <td>80-125 microns</td> </tr> <tr> <td>Theoretical coverage</td> <td>7.5-4 m<sup>2</sup>/Lit</td> </tr> <tr> <td></td> <td>Practical coverage depends on loss factor</td> </tr> <tr> <td>Touch dry</td> <td>30 min. at 20 °c</td> </tr> <tr> <td>Hard dry</td> <td>4 hrs. at 20 °c</td> </tr> <tr> <td>Thermal resistance</td> <td>Max. 60 °c (dry exposure)</td> </tr> <tr> <td></td> <td>Non-Continuous Max. 65 °c</td> </tr> </table>	Finish	Semi flat – Semi gloss	Color	Upon request	Solid by volume	55±5%	Specific Gravity	1.35±0.1 gr/cm <sup>3</sup>	Flash point	30 °c	Recommended D.F.T.	80-125 microns	Theoretical coverage	7.5-4 m <sup>2</sup> /Lit		Practical coverage depends on loss factor	Touch dry	30 min. at 20 °c	Hard dry	4 hrs. at 20 °c	Thermal resistance	Max. 60 °c (dry exposure)		Non-Continuous Max. 65 °c
Finish	Semi flat – Semi gloss																								
Color	Upon request																								
Solid by volume	55±5%																								
Specific Gravity	1.35±0.1 gr/cm <sup>3</sup>																								
Flash point	30 °c																								
Recommended D.F.T.	80-125 microns																								
Theoretical coverage	7.5-4 m <sup>2</sup> /Lit																								
	Practical coverage depends on loss factor																								
Touch dry	30 min. at 20 °c																								
Hard dry	4 hrs. at 20 °c																								
Thermal resistance	Max. 60 °c (dry exposure)																								
	Non-Continuous Max. 65 °c																								

Technical Data Sheet: Ref: TDS-HPC-0001-V02

Date of issue: June 2017

[www.kansaipaint.ir](http://www.kansaipaint.ir)

---

## APPLICATION

Application method	Air/Airless spray, Brush, Roller
Surface temperature	10-50 °c
Mixing ratio	Single pack
Packaging	25 KG
Thinner/cleaner	A840-0212
Pot Life	N/A
Recoat interval	Min 1 hrs. at 20° c Max indefinite Recoating intervals related to later conditions of exposure
Nozzle orifice	0.018"-0.021"
Nozzle pressure	150 bar/2175 psi Airless spray is indicative and subject to adjustment
Application condition	Apply only on a dry and clean surface with a temperature above the dew point to avoid condensation. In confined spaces provide adequate ventilation during application and drying.

---

## SURFACE PREPARATION

The surface must be clean, dry and free from rust, mill scale, salt and any other contaminants.

---

## SAFETY PRECAUTIONS

Detail information is given on Material Safety Data Sheet (MSDS). Avoid inhalation of spray mist or vapor. Avoid skin and eye contact. Paint contacted with skin should be immediately removed with water and/or suitable cleanser. Eyes should be flushed with water and seek immediate medical attention. Since this product contains flammable solvents, keep away from sparks and open flames. Application and handling of this product should be in compliance with relevant national regulations.

---

## STORAGE

Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept tightly closed. Store conditions shall be in accordance with national regulations.

---

## SHELF LIFE

12 months from date of production

---

**DISCLAIMER:** The information given on this sheet is to the best of our knowledge and accurate at the time of issuing. Since conditions of use are beyond the manufacturer's control information contained herein is without warranty implied or otherwise and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development.