



kansai paint

Kansai Paint Iranian

Technical Data Sheet: Ref: TDS-HPC-0001-V02

Date of issue: June 2017

www.kansaipaint.ir

A322-1001

ALKYD IRON OXIDE PRIMER (Alkyd anti rust)

GENERIC TYPE	Alkyd																				
DESCRIPTION	A322-1001 is a general purpose red oxide primer based on Long oil alkyd resin with fairly good penetration into rough and porous substrate.																				
RECOMMENDED USE	For use on structural steel to be coated with alkyd based Finish coat in mild environment.																				
FEATURE	<ul style="list-style-type: none">-Rust preventing-Excellent spray ability-Excellent flexibility-Good resistance in mildly to moderately corrosive environment																				
PHYSICAL PROPERTIES	<table><tr><td>Finish</td><td>Flat</td></tr><tr><td>Color</td><td>Red</td></tr><tr><td>Solid by volume</td><td>55±5%</td></tr><tr><td>Specific Gravity</td><td>1.45±0.1 gr/cm³</td></tr><tr><td>Flash point</td><td>38 °c</td></tr><tr><td>Recommended D.F.T.</td><td>60-80 microns</td></tr><tr><td>Theoretical coverage</td><td>10-6.25 m² /Lit Practical coverage depends on loss factor</td></tr><tr><td>Touch dry</td><td>4 hrs. at 20 °c</td></tr><tr><td>Hard dry</td><td>16 hrs. at 20 °c</td></tr><tr><td>Thermal resistance</td><td>Max. 100 °c (dry exposure)</td></tr></table>	Finish	Flat	Color	Red	Solid by volume	55±5%	Specific Gravity	1.45±0.1 gr/cm ³	Flash point	38 °c	Recommended D.F.T.	60-80 microns	Theoretical coverage	10-6.25 m ² /Lit Practical coverage depends on loss factor	Touch dry	4 hrs. at 20 °c	Hard dry	16 hrs. at 20 °c	Thermal resistance	Max. 100 °c (dry exposure)
Finish	Flat																				
Color	Red																				
Solid by volume	55±5%																				
Specific Gravity	1.45±0.1 gr/cm ³																				
Flash point	38 °c																				
Recommended D.F.T.	60-80 microns																				
Theoretical coverage	10-6.25 m ² /Lit Practical coverage depends on loss factor																				
Touch dry	4 hrs. at 20 °c																				
Hard dry	16 hrs. at 20 °c																				
Thermal resistance	Max. 100 °c (dry exposure)																				

Technical Data Sheet: Ref: TDS-HPC-0001-V02

Date of issue: June 2017

www.kansaipaint.ir

APPLICATION

Application method	Air/Airless spray, Brush, Roller
Surface temperature	10-50 °c
Mixing ratio	Single pack
Packaging	25 KG
Thinner/cleaner	A840-0322
Pot Life	N/A
Recoat interval	Min 8 hrs. at 20° c Max 30 days at 20° c Recoating intervals related to later conditions of exposure
Nozzle orifice	0.019"-0.021"
Nozzle pressure	150 bar/2175 psi Airless spray is indicative and subject to adjustment
Application condition	Apply only on a dry and clean surface with a temperature above the dew point to avoid condensation. In confined spaces provide adequate ventilation during application and drying.

SURFACE PREPARATION

For new steel abrasive blasting to minimum Sa2, alternatively power tool cleaning to St-3. For maintenance remove oil and grease and any other contaminants by suitable detergent and consequently by high-pressure fresh water cleaning. Remove all rust and loose material by abrasive blasting or power-tool cleaning, dust off residues before painting.

SAFETY PRECAUTIONS

Detail information is given on Material Safety Data Sheet (MSDS). Avoid inhalation of spray mist or vapor. Avoid skin and eye contact. Paint contacted with skin should be immediately removed with water and/or suitable cleanser. Eyes should be flushed with water and seek immediate medical attention. Since this product contains flammable solvents, keep away from sparks and open flames. Application and handling of this product should be in compliance with relevant national regulations.

STORAGE

Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept tightly closed. Store conditions shall be in accordance with national regulations.

SHELF LIFE

12 months from date of production

DISCLAIMER: The information given on this sheet is to the best of our knowledge and accurate at the time of issuing. Since conditions of use are beyond the manufacturer's control information contained herein is without warranty implied or otherwise and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development.