

Technical Data Sheet: Ref: TDS-HPC-0001-V02

www.kansaipaint.ir

Date of issue: June 2017

A414-1001

POLYURETHANE ANTY-CROSSIVE PRIMER&INTERMEDIATE

GENERIC TYPE	Polyurethane	
DESCRIPTION	A414-1001 is two components, aromatic isocyanate cured polyurethane primer or intermediate.	
RECOMMENDED USE	As an anti-corrosive primer on industrial structures, tanks, chemical & petrochemical atmospheric environments, pulp& paper industry, food & beverage plants, bridge & marine structures on ships, barge & offshore platforms, also on concrete substrate.	
FEATURES	<ul style="list-style-type: none"> -Good adhesion on metal & concrete surfaces -Excellent flexibility -Corrosion resistance properties -Water & chemical resistance 	
PHESICAL PROPERTIES	Finish	Flat - Semi flat
	Color	Upon request
	Solid by volume	53±5%
	Specific Gravity	1.3±0.1 gr/cm ³
	Flash point	30 °c
	Recommended D.F.T.	80-100 microns
	Theoretical coverage	7.25-4.8 m ² / Lit
		Practical coverage depends on loss factor
	Touch dry	3 hrs. at 20° c
	Hard dry	24 hrs. at 20° c
	Full Cured	7 days. at 20° c
	Thermal resistance	Max. 120° c (dry exposure)

Technical Data Sheet: Ref: TDS-HPC-0001-V02

www.kansaipaint.ir

Date of issue: June 2017

APPLICATION

Application method	Air/Airless spray, Brush, Roller
Surface temperature	10-40 °c
Mixing ratio(by weight)	5:1
Packaging(A+B)	20KG+4KG
Hardener(B)	A275-2007-50
Thinner/Cleaner	A840-0414
Recoat interval	Min 16 hrs.at 20 °c , Max 14 days .at 20 °c
Pot Life	5 hrs. at 20 °c
Application condition	Apply only on a dry and clean surface with a temperature above the dew point to avoid condensation Environment Temperature should be 10 °C min and 40 °C max and Relative humidity: 80% maximum.
Nozzle orifice	0.017"-0.021"
Nozzle pressure	150 bar/2175 psi Airless spray is indicative and subject to adjustment

SURFACE PREPRATION

- All surfaces to be coated should be completely clean, dry and free from contamination. Surface preparation method shall be in accordance with ISO 8504: 2000.
- Remove salt and other water-soluble contaminants by fresh water.
- Remove oil and grease with suitable detergent or solvent (SSPC-SP-1).
- Remove rust, mill scale and other loose material completely by abrasive blasting (ISO 8501-1:2007 Sa 2 1/2 or SSPC SP-10).

SAFETY PRECAUTIONS

Detail information is given on Material Safety Data Sheet (MSDS). Avoid inhalation of spray mist or vapor. Avoid skin and eye contact. Paint contacted with skin should be immediately removed with water and/or suitable cleanser. Eyes should be flushed with water and seek immediate medical attention. Since this product contains flammable solvents, keep away from sparks and open flames. Application and handling of this product should be in compliance with relevant national regulations.

STORAGE

Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept tightly closed. Store conditions shall be in accordance with national regulations.

SHELF LIFE

12 months from date of production.

DISCLAIMER: The information given on this sheet is to the best of our knowledge and accurate at the time of issuing. Since conditions of use are beyond the manufacturer's control information contained herein is without warranty implied or otherwise and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development.