

Technical Data Sheet: Ref: TDS-HPC-0001-V02

www.kansaipaint.ir

Date of issue: June 2017

A570-3008

POLYAMINE CURED ANTI STATIC EPOXY FLOORING

GENERIC TYPE	Epoxy																								
DESCRIPTION	A570-3008 is a two components, polyamine cured, solvent free epoxy floor coating. This paint is electrically Conductive so that static charges are avoided. This achieve leakage resistance of 104-106 ohm as measured according to DIN 51953 and therefore satisfy the Directives for avoiding ignition risks resulting from electrostatic charges of the employer's liability insurance of the chemical industry.																								
RECOMMENDED USE	As a suitable floor coating on concrete floors subjects to continuous mechanical wear and where static charge resistance is required.																								
FEATURES	<ul style="list-style-type: none"> -High electrical conductivity -Excellent mechanical strength -High Oil resistance -High chemical resistance against weak acids & alkalis -Easy application 																								
PHESICAL PROPERTIES	<table border="1"> <tr> <td>Finish</td> <td>Gloss</td> </tr> <tr> <td>Color</td> <td>Gray</td> </tr> <tr> <td>Solid by volume</td> <td>98±2%</td> </tr> <tr> <td>Specific Gravity</td> <td>1.45±0.1 gr/cm3</td> </tr> <tr> <td>Flash point</td> <td>> 60 °c</td> </tr> <tr> <td>Recommended D.F.T.</td> <td>1000-3000 microns</td> </tr> <tr> <td>Theoretical coverage</td> <td>1-0.32 m² / Lit</td> </tr> <tr> <td></td> <td>Practical coverage depends on loss factor</td> </tr> <tr> <td>Touch dry (man traffic)</td> <td>24 hrs. at 20° c</td> </tr> <tr> <td>Hard dry (vehicle traffic)</td> <td>72 hrs. at 20° c</td> </tr> <tr> <td>Full Cured</td> <td>7 days. at 20° c</td> </tr> <tr> <td>To Recoat</td> <td>Min 16 hrs. at 20° c , Max 96 hrs. at 20° c</td> </tr> </table>	Finish	Gloss	Color	Gray	Solid by volume	98±2%	Specific Gravity	1.45±0.1 gr/cm3	Flash point	> 60 °c	Recommended D.F.T.	1000-3000 microns	Theoretical coverage	1-0.32 m ² / Lit		Practical coverage depends on loss factor	Touch dry (man traffic)	24 hrs. at 20° c	Hard dry (vehicle traffic)	72 hrs. at 20° c	Full Cured	7 days. at 20° c	To Recoat	Min 16 hrs. at 20° c , Max 96 hrs. at 20° c
Finish	Gloss																								
Color	Gray																								
Solid by volume	98±2%																								
Specific Gravity	1.45±0.1 gr/cm3																								
Flash point	> 60 °c																								
Recommended D.F.T.	1000-3000 microns																								
Theoretical coverage	1-0.32 m ² / Lit																								
	Practical coverage depends on loss factor																								
Touch dry (man traffic)	24 hrs. at 20° c																								
Hard dry (vehicle traffic)	72 hrs. at 20° c																								
Full Cured	7 days. at 20° c																								
To Recoat	Min 16 hrs. at 20° c , Max 96 hrs. at 20° c																								

Technical Data Sheet: Ref: TDS-HPC-0001-V02

www.kansaipaint.ir

Date of issue: June 2017

APPLICATION

Application method	Putty knife, trowel, Roller
Surface temperature	3 °C min. above dew point
Mixing ratio(by weight)	4:1
Packaging(A+B)	16KG+4KG
Hardener(B)	A275-2006
Washing Thinner	A840-0570
Pot Life	(40 min. at 15 °c) – (30 min. at 25 °c) – (20 min. at 35 °c)
Application condition	Environment Temperature should be 10 °C min and 40 °C max

SURFACE PREPARATION

A. NEW WORK:

1. Concrete Floors:

1.1. The concrete should have been cured for at least 28 days and have moisture content of less than 4%.

1.2. Floors should be sound and free from loose materials and any contamination such as oil and grease that would prevent coating adhesion.

1.3. Excess laitance deposits should be removed by light mechanical scrubbing, grinding or grit/captive blasting followed by vacuum cleaning to remove dust debris.

B. OLD CONCRETE FLOORS:

1.1. A sound, clean substrate is essential to achieve maximum adhesion.

1.2. Excess laitance deposits should be removed by light mechanical scrubbing, grinding or grit/captive blasting followed by vacuum cleaning to remove dust debris.

C. Filling:

1. Fill the dents and cracks in the surface with mixture of 1 Part of Kansai Epoxy SF Floor Primer and 2 parts of Kansai Fine Aggregate or with Kansai Epoxy filler.

APPLICATION PROCEDURE

1.1. Mix the base and hardener of Kansai Epoxy anti-static Floor coat in the given proportion.

1.2. Stir using slow speed drill and paddle.

1.3. Pour the mixture on the floor and spread using medium pile hair roller or rubber spreader.

1.4. Ensure any loose hair is removed from the roller.

1.5. Apply at 200 μ to a smooth continuous film.

It is very important to pierce the coating with a spiked roller, after achieving the desired thickness, to avoid air bubbles.

1.6. On complete drying, the whole surface to be thoroughly cleaned by means of brush or vacuum and remove all loose grains.

1.7. Finish off by applying second coat by medium pile hair roller, It is important that continuous film is achieved and the rough surface, caused by the aggregate, is completely sealed.

CAUTIONS

- Friable and powdery surfaces require special care before painting; if in doubt, contact manufacturer.

- For health reasons avoid dusting when preparing fiber cement surfaces. Keep surfaces wet and wash off residues with water.

- Do not paint under conditions of frost, dew, rain or fog or inclement weather.

Note: Painting under the above conditions may affect the performance of the paint film.

- Avoid painting during inclement weather or if temperature is below 10 °C.

- To ensure colors on a project are consistent check if the batch numbers and/or colors supplied are the same.

Technical Data Sheet: Ref: TDS-HPC-0001-V02

www.kansaipaint.ir

Date of issue: June 2017

STORAGE

Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept tightly closed. Store conditions shall be in accordance with national regulations.

SHELF LIFE

12 months from date of production.

SAFETY PRECAUTIONS

- Keep out of reach of children.
- Ensure good ventilation during application and drying.
- In case of skin contact, wash with soap and water or a recognized skin cleaner.
- Avoid contact with eyes – In case of contact, rinse eyes immediately with plenty of water and seek medical advice if symptoms persist.
- Harmful if swallowed. Do not induce vomiting. Seek medical attention.
- Do not smoke while painting.
- Flammable. Store in a cool dry place away from heat and sparks.
- Refer to Material Safety Data Sheet for complete information.

DISCLAIMER: The information given on this sheet is to the best of our knowledge and accurate at the time of issuing. Since conditions of use are beyond the manufacturer's control information contained herein is without warranty implied or otherwise and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development.