

Technical Data Sheet: Ref: TDS-HPC-0001-V02

www.kansaipaint.ir

Date of issue: June 2017

A570-3009

POLYAMINE CURED SELF LEVELING EPOXY FLOORING

GENERIC TYPE	Epoxy																								
DESCRIPTION	A570-3009 is a two components, polyamine cured, solvent free epoxy floor coating with an excellent abrasion resistance on concrete surfaces. And it is a self-leveling product, leaving a seamless surface. SLE is used as a topcoat as part of a complete system in atmospheric environment. It has excellent chemical and impact resistance.																								
RECOMMENDED USE	SLE as topcoat for floor surfaces is recommended for heavy duty parking areas, ramps, loading bays, garages, chemical manufacturing plants, warehouses with forklift where a lasting protection from abrasion and a good smooth surface is required.																								
FEATURES	<ul style="list-style-type: none"> -Excellent mechanical strength -High Oil resistance -High chemical resistance against weak acids & alkalis -Outstanding application properties -Abrasion Resistant 																								
PHYSICAL PROPERTIES	<table border="0"> <tr> <td>Finish</td> <td>Gloss – High Gloss</td> </tr> <tr> <td>Color</td> <td>Upon request</td> </tr> <tr> <td>Solid by volume</td> <td>98±2%</td> </tr> <tr> <td>Specific Gravity</td> <td>1.55±0.1 gr/cm³</td> </tr> <tr> <td>Flash point</td> <td>> 65 °c</td> </tr> <tr> <td>Recommended D.F.T.</td> <td>1000-3000 microns</td> </tr> <tr> <td>Theoretical coverage</td> <td>1-0.32 m² / Lit</td> </tr> <tr> <td></td> <td>Practical coverage depends on loss factor</td> </tr> <tr> <td>Touch dry (man traffic)</td> <td>24 hrs. at 20° c</td> </tr> <tr> <td>Hard dry (vehicle traffic)</td> <td>72 hrs. at 20° c</td> </tr> <tr> <td>Full Cured</td> <td>7 days. at 20° c</td> </tr> <tr> <td>To Recoat</td> <td>Min 16 hrs. at 20° c , Max 96 hrs. at 20° c</td> </tr> </table>	Finish	Gloss – High Gloss	Color	Upon request	Solid by volume	98±2%	Specific Gravity	1.55±0.1 gr/cm ³	Flash point	> 65 °c	Recommended D.F.T.	1000-3000 microns	Theoretical coverage	1-0.32 m ² / Lit		Practical coverage depends on loss factor	Touch dry (man traffic)	24 hrs. at 20° c	Hard dry (vehicle traffic)	72 hrs. at 20° c	Full Cured	7 days. at 20° c	To Recoat	Min 16 hrs. at 20° c , Max 96 hrs. at 20° c
Finish	Gloss – High Gloss																								
Color	Upon request																								
Solid by volume	98±2%																								
Specific Gravity	1.55±0.1 gr/cm ³																								
Flash point	> 65 °c																								
Recommended D.F.T.	1000-3000 microns																								
Theoretical coverage	1-0.32 m ² / Lit																								
	Practical coverage depends on loss factor																								
Touch dry (man traffic)	24 hrs. at 20° c																								
Hard dry (vehicle traffic)	72 hrs. at 20° c																								
Full Cured	7 days. at 20° c																								
To Recoat	Min 16 hrs. at 20° c , Max 96 hrs. at 20° c																								

Technical Data Sheet: Ref: TDS-HPC-0001-V02

www.kansaipaint.ir

Date of issue: June 2017

APPLICATION

Application method	Putty knife, trowel, Roller
Surface temperature	3 °C min. above dew point
Mixing ratio(by weight)	4:1
Packaging(A+B)	16KG+4KG
Hardener(B)	A275-2006
Washing Thinner	A840-0570
Pot Life	(45 min. at 15 °c) – (30 min. at 25 °c) – (20 min. at 35 °c)
Application condition	Environment Temperature should be 10 °C min and 40 °C max

SURFACE PREPARATION

A. NEW WORK:

1. Concrete Floors:

- 1.1. The concrete should have been cured for at least 28 days and have moisture content of less than 4%.
- 1.2. Floors should be sound and free from loose materials and any contamination such as oil and grease that would prevent coating adhesion.
- 1.3. Excess laitance deposits should be removed by light mechanical scrubbing, grinding or grit/captive blasting followed by vacuum cleaning to remove dust debris.

B. OLD CONCRETE FLOORS:

- 1.1. A sound, clean substrate is essential to achieve maximum adhesion.
- 1.2. Excess laitance deposits should be removed by light mechanical scrubbing, grinding or grit/captive blasting followed by vacuum cleaning to remove dust debris.

C. Filling:

1. Fill the dents and cracks in the surface with mixture of 1 Part of Kansai Epoxy SF Floor Primer and 2 parts of Kansai Fine Aggregate or with Kansai Epoxy filler.

Technical Data Sheet: Ref: TDS-HPC-0001-V02

www.kansaipaint.ir

Date of issue: June 2017

APPLICATION PROCEDURE

A. Anti-Skid:

- 1.1. Mix the base and hardener of Kansai Epoxy SF Floor Topcoat in the given proportion.
- 1.2. Stir using slow speed drill and paddle.
- 1.3. Pour the mixture on the floor and spread using medium pile hair roller or rubber spreader.
- 1.4. Ensure any loose hair is removed from the roller.
- 1.5. Apply at 200 μ to a smooth continuous film.

It is very important to pierce the coating with a spiked roller, after achieving the desired thickness, to avoid air bubbles.

- 1.6. After 15 minutes, sprinkle Kansai Medium Aggregates to completely cover the base coat.
- 1.7. On complete drying, the whole surface to be thoroughly cleaned by means of brush or vacuum and remove all loose grains.
- 1.8. Finish off by applying second coat by medium pile hair roller, It is important that continuous film is achieved and the rough surface, caused by the aggregate, is completely sealed.

B. Self-Leveling Preparation (1 mm thick coat)

- 1.1. Mix the base and hardener of Kansai Epoxy SF Floor Topcoat in the given proportion.
- 1.2. Pour the mixture to another container and add equal part by weight of Kansai Fine aggregate while continuing stirring using power mixer with paddle blade. Mix 3 minutes.
- 1.3. Immediately pour this mixture onto a well primed surface.
- 1.4. Using steel serrated trowel spread the mixture well on to the surface to a thickness of 1mm.
- 1.5. It is very important to pierce the coating with a spiked roller, after achieving the desired thickness, to avoid air bubbles.

C. Application with trowel:

After the Sealer application, when cured, apply a scraper coat in order to fill all imperfections, and to some Degree level out the smaller valley and to further improve on the sealer effect to avoid bubbles. Use a steel trowel where there are adjustable pins or wheels at both ends of the trowel, adjust the specified WFT=DFT. One team is pouring out the ready mixed SLE Coating, next team doing the spreading, moving the SLE Coating in one direction but length by length.

CAUTIONS

- Friable and powdery surfaces require special care before painting; if in doubt, contact manufacturer.
 - For health reasons avoid dusting when preparing fiber cement surfaces. Keep surfaces wet and wash off residues with water.
 - Do not paint under conditions of frost, dew, rain or fog or inclement weather.
- Note:** Painting under the above conditions may affect the performance of the paint film.
- Avoid painting during inclement weather or if temperature is below 10 °C.
 - To ensure colors on a project are consistent check if the batch numbers and/or colors supplied are the same.

STORAGE

Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept tightly closed. Store conditions shall be in accordance with national regulations.

SHELF LIFE

12 months from date of production.

Technical Data Sheet: Ref: TDS-HPC-0001-V02

www.kansaipaint.ir

Date of issue: June 2017

**SAFETY
PRECAUTIONS**

- Keep out of reach of children.
- Ensure good ventilation during application and drying.
- In case of skin contact, wash with soap and water or a recognized skin cleaner.
- Avoid contact with eyes – In case of contact, rinse eyes immediately with plenty of water and seek medical advice if symptoms persist.
- Harmful if swallowed. Do not induce vomiting. Seek medical attention.
- Do not smoke while painting.
- Flammable. Store in a cool dry place away from heat and sparks.
- Refer to Material Safety Data Sheet for complete information.

DISCLAIMER: The information given on this sheet is to the best of our knowledge and accurate at the time of issuing. Since conditions of use are beyond the manufacturer's control information contained herein is without warranty implied or otherwise and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development.