

Technical Data Sheet: Ref: TDS-HPC-0001-V02

Date of issue: June 2017

[www.kansaipaint.ir](http://www.kansaipaint.ir)

## A628-3002

### HIGH RESISTANT COATING IN AMBIENT TEMPRATURE CURING

|                            |   |  |
|----------------------------|---|--|
| <b>GENERIC TYPE</b>        | Heat Resistant  |  |
| <b>DESCRIPTION</b>         | A628-3001 is a special synthetic resin based on heat resistant coating with aluminum pigment up to 600 °c. which is air drying at ambient temperature.        |  |
| <b>RECOMMENDED USE</b>     | For long-term protection of smoke stacks, exhaust pipes, hot pipe lines, stove. boiler, motor heater and other hot surfaces Up to 600°c is used.              |  |
| <b>FEATURE</b>             | <ul style="list-style-type: none"> <li>-High temperature resistance-Good spray ability</li> <li>-Rust preventing</li> <li>-Excellent spray ability</li> </ul> |  |
| <b>PHYSICAL PROPERTIES</b> | Finish  | Shiny  |
|                            | Color   | Aluminum   |
|                            | Solid by volume   | 35±5%  |
|                            | Specific Gravity  | 1.05±0.1 gr/cm3  |
|                            | Flash point   | 26 °c  |
|                            | Recommended D.F.T.  | 15-20 Microns per one coat   |
|                            | Theoretical coverage  | 26.6-15 m <sup>2</sup> /Lit<br>Practical coverage depends on loss factor |
|                            | Touch dry   | 15 min. at 20°c  |
|                            | Hard dry  | 4 hrs. at 20°c   |
|                            | Thermal resistance  | Max 600°c  |

Technical Data Sheet: Ref: TDS-HPC-0001-V02

Date of issue: June 2017

[www.kansaipaint.ir](http://www.kansaipaint.ir)

## APPLICATION

|                       |  |
|-----------------------|--|
| Application method    | Air/Airless spray, Brush, Roller   |
| Surface temperature   | 10-40 °c   |
| Mixing ratio          | Single pack  |
| Packaging             | 20 KG – 4 KG   |
| Thinner/cleaner       | A840-0628  |
| Pot Life              | N/A  |
| Recoat interval       | Min 1 hrs. at 20° c<br>Max indefinite<br>Recoating intervals related to later conditions of exposure   |
| Nozzle orifice        | 0.018"-0.021"  |
| Nozzle pressure       | 128 bar/1800 psi<br>Airless spray is indicative and subject to adjustment  |
| Application condition | Apply only on a dry and clean surface with a temperature above the dew point to avoid condensation. In confined spaces provide adequate ventilation during application and drying. |

## SURFACE PREPARATION

- All surfaces to be coated should be completely clean, dry and free from contamination. Surface preparation method shall be in accordance with ISO 8504: 2000.
- Remove salt and other water-soluble contaminants by fresh water.
- Remove oil and grease with suitable detergent or solvent (SSPC-SP-1).
- Remove rust, mill scale and other loose material completely by abrasive blasting (ISO 8501-1:2007 Sa 2 1/2 or SSPC SP-10).

## SAFETY PRECAUTIONS

Detail information is given on Material Safety Data Sheet (MSDS). Avoid inhalation of spray mist or vapor. Avoid skin and eye contact. Paint contacted with skin should be immediately removed with water and/or suitable cleanser. Eyes should be flushed with water and seek immediate medical attention. Since this product contains flammable solvents, keep away from sparks and open flames. Application and handling of this product should be in compliance with relevant national regulations.

## GENERAL REMARKS

- The maximum DFT which should be applied before heating is 20 microns (0.6 mils) otherwise blistering will occur. Two or more coats cannot be applied without heating between coats.
- To prevent moisture condensation during application, surface temperature must be at least 3 °C above the dew point.
- For satisfactory cure, air and surface temperature must be above 10 °C.
- The surface profile should be less than 12 microns.

## STORAGE

Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept tightly closed. Store conditions shall be in accordance with national regulations.

## SHELF LIFE

6 months from date of production

DISCLAIMER: The information given on this sheet is to the best of our knowledge and accurate at the time of issuing. Since conditions of use are beyond the manufacturer's control information contained herein is without warranty implied or otherwise and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development.