

Technical Data Sheet: Ref: TDS-HPC-0001-V02

[www.kansaipaint.ir](http://www.kansaipaint.ir)

Date of issue: June 2017

## A560-2001

### EPOXY ESTER INTERMEDIATE COATING

<b>GENERIC TYPE</b>	Epoxy Ester																						
<b>DESCRIPTION</b>	A560-2001 is a single pack intermediate or topcoat based on air drying epoxy ester resin.																						
<b>RECOMMENDED USE</b>	As a coating on primer in industrial and marine structures such as refineries, petrochemical plants, bridges, tanks and water sewage plants.																						
<b>FEATURES</b>	<ul style="list-style-type: none"> <li>-High corrosion resistance</li> <li>-Good adhesion to subsequent coats</li> <li>-Toughness and durability of film</li> <li>-Good process ability</li> </ul>																						
<b>PHESICAL PROPERTIES</b>	<table border="0"> <tr> <td>Finish</td> <td>Semi flat - Semi Gloss</td> </tr> <tr> <td>Color</td> <td>Upon request</td> </tr> <tr> <td>Solid by volume</td> <td>53±5%</td> </tr> <tr> <td>Specific Gravity</td> <td>1.35±0.1 gr/cm<sup>3</sup></td> </tr> <tr> <td>Flash point</td> <td>26 °c</td> </tr> <tr> <td>Recommended D.F.T.</td> <td>100-125 microns</td> </tr> <tr> <td>Theoretical coverage</td> <td>5.8-4 m<sup>2</sup>/ Lit</td> </tr> <tr> <td></td> <td>Practical coverage depends on loss factor</td> </tr> <tr> <td>Touch dry</td> <td>1 hrs. at 20°c</td> </tr> <tr> <td>Hard dry</td> <td>20 hrs. at 20°c</td> </tr> <tr> <td>Thermal resistance</td> <td>Max. 140°c (dry exposure)</td> </tr> </table>	Finish	Semi flat - Semi Gloss	Color	Upon request	Solid by volume	53±5%	Specific Gravity	1.35±0.1 gr/cm <sup>3</sup>	Flash point	26 °c	Recommended D.F.T.	100-125 microns	Theoretical coverage	5.8-4 m <sup>2</sup> / Lit		Practical coverage depends on loss factor	Touch dry	1 hrs. at 20°c	Hard dry	20 hrs. at 20°c	Thermal resistance	Max. 140°c (dry exposure)
Finish	Semi flat - Semi Gloss																						
Color	Upon request																						
Solid by volume	53±5%																						
Specific Gravity	1.35±0.1 gr/cm <sup>3</sup>																						
Flash point	26 °c																						
Recommended D.F.T.	100-125 microns																						
Theoretical coverage	5.8-4 m <sup>2</sup> / Lit																						
	Practical coverage depends on loss factor																						
Touch dry	1 hrs. at 20°c																						
Hard dry	20 hrs. at 20°c																						
Thermal resistance	Max. 140°c (dry exposure)																						

Technical Data Sheet: Ref: TDS-HPC-0001-V02

[www.kansaipaint.ir](http://www.kansaipaint.ir)

Date of issue: June 2017

## APPLICATION

Application method	Air/Airless spray, Brush, Roller
Surface temperature	10-40 °c
Mixing ratio	Single pack
Packaging	25KG
Thinner/Cleaner	A840-0560
Recoat interval	Min 12 hrs.at 20 °c, Max 30 days. at 20 °c
Pot Life	N/A
Application condition	Apply only on a dry and clean surface with a temperature above the dew point to avoid condensation Environment Temperature should be 10 °C min and 40 °C max and Relative humidity: 80% maximum.
Nozzle orifice	0.019"-0.021"
Nozzle pressure	150 bar/2175 psi Airless spray is indicative and subject to adjustment

## SURFACE PREPRATION

The surface must be clean and dry. Any contamination such as dirt, grease, oil, salt and any other foreign materials should be removed.

## SAFETY PRECAUTIONS

Detail information is given on Material Safety Data Sheet (MSDS). Avoid inhalation of spray mist or vapor. Avoid skin and eye contact. Paint contacted with skin should be immediately removed with water and/or suitable cleanser. Eyes should be flushed with water and seek immediate medical attention. Since this product contains flammable solvents, keep away from sparks and open flames. Application and handling of this product should be in compliance with relevant national regulations.

## STORAGE

Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept tightly closed. Store conditions shall be in accordance with national regulations.

## SHELF LIFE

12 months from date of production.

**DISCLAIMER:** The information given on this sheet is to the best of our knowledge and accurate at the time of issuing. Since conditions of use are beyond the manufacturer's control information contained herein is without warranty implied or otherwise and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development.