



kansai paint

Kansai Paint Iranian

Technical Data Sheet: Ref: TDS-HPC-0001-V02

www.kansaipaint.ir

Date of issue: June 2017

A570-1010

POLYAMIDE CURED EPOXY ZINC RICH PRIMER

GENERIC TYPE	Epoxy																						
DESCRIPTION	A570-1010 is a two component, polyamide cured epoxy Primer, containing zinc dust as corrosion inhabiting pigment.																						
RECOMMENDED USE	As a versatile long-life primer on steel, suitable for application on industrial structures to be exposed in severe corrosive atmosphere.																						
FEATURES	<ul style="list-style-type: none">-Suitable as prefabrication primer-Good cutting and welding properties-Suitable as a first coat in various paint systems-Corrosion resistance in moderately to severely environment																						
PHESICAL PROPERTIES	<table><tr><td>Finish</td><td>Matt</td></tr><tr><td>Color</td><td>Gray</td></tr><tr><td>Solid by volume</td><td>60±5%</td></tr><tr><td>Specific Gravity</td><td>2.55±0.1 gr/cm³</td></tr><tr><td>Flash point</td><td>29 °c</td></tr><tr><td>Recommended D.F.T.</td><td>50-75 microns</td></tr><tr><td>Theoretical coverage</td><td>13-7.33 m² / Lit Practical coverage depends on loss factor</td></tr><tr><td>Zinc content in dry film</td><td>60±5% by weight</td></tr><tr><td>Touch dry</td><td>2 hrs. at 20 °c</td></tr><tr><td>Full Cured</td><td>7 days. at 20 °c</td></tr><tr><td>Thermal resistance</td><td>Max. 150 °c (dry exposure)</td></tr></table>	Finish	Matt	Color	Gray	Solid by volume	60±5%	Specific Gravity	2.55±0.1 gr/cm ³	Flash point	29 °c	Recommended D.F.T.	50-75 microns	Theoretical coverage	13-7.33 m ² / Lit Practical coverage depends on loss factor	Zinc content in dry film	60±5% by weight	Touch dry	2 hrs. at 20 °c	Full Cured	7 days. at 20 °c	Thermal resistance	Max. 150 °c (dry exposure)
Finish	Matt																						
Color	Gray																						
Solid by volume	60±5%																						
Specific Gravity	2.55±0.1 gr/cm ³																						
Flash point	29 °c																						
Recommended D.F.T.	50-75 microns																						
Theoretical coverage	13-7.33 m ² / Lit Practical coverage depends on loss factor																						
Zinc content in dry film	60±5% by weight																						
Touch dry	2 hrs. at 20 °c																						
Full Cured	7 days. at 20 °c																						
Thermal resistance	Max. 150 °c (dry exposure)																						



kansai paint

Kansai Paint Iranian

Technical Data Sheet: Ref: TDS-HPC-0001-V02

www.kansaipaint.ir

Date of issue: June 2017

APPLICATION

Application method	Air/Airless spray, Brush, Roller
Surface temperature	10-40 °c
Mixing ratio(by weight)	9:1
Packaging(A+B)	27KG+3KG
Hardener(B)	A275-2008-50
Thinner/Cleaner	A840-0570
Recoat interval	Min 24 hrs.at 20 °c, Max 10 days. at 20 °c
Pot Life	8 hrs. at 20 °c
Application condition	Apply only on a dry and clean surface with a temperature above the dew point to avoid condensation Environment Temperature should be 10 °C min and 40 °C max and Relative humidity: 80% maximum.
Nozzle orifice	0.019"-0.021"
Nozzle pressure	150 bar/2175 psi Airless spray is indicative and subject to adjustment

SURFACE PREPRATION

Surface should be free from oil, grease, dust and mill scale by solvent cleaning or high pressure fresh water hosing and finally sand blasting up to Sa2½ or SSPC-SP10.

SAFETY PRECAUTIONS

Detail information is given on Material Safety Data Sheet (MSDS). Avoid inhalation of spray mist or vapor. Avoid skin and eye contact. Paint contacted with skin should be immediately removed with water and/or suitable cleanser. Eyes should be flushed with water and seek immediate medical attention. Since this product contains flammable solvents, keep away from sparks and open flames. Application and handling of this product should be in compliance with relevant national regulations.

STORAGE

Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept tightly closed. Store conditions shall be in accordance with national regulations.

SHELF LIFE

6 months from date of production.

DISCLAIMER: The information given on this sheet is to the best of our knowledge and accurate at the time of issuing. Since conditions of use are beyond the manufacturer's control information contained herein is without warranty implied or otherwise and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development.