



kansai paint

Kansai Paint Iranian

Technical Data Sheet: Ref: TDS-HPC-0001-V02

www.kansaipaint.ir

Date of issue: June 2017

A322-3008

ALKYD TOP COAT (Matt)

GENERIC TYPE

Alkyd

DESCRIPTION

A322-3008 is a versatile finish coat based on alkyd enamel which forms a weather resistant coating .it is flexible and resistant to saltwater and spillage of mineral oil and other aliphatic hydrocarbons.

RECOMMENDED USE

As a general purpose finishing coat in alkyd system on exterior and interior steel and woodwork in mildly to moderately corrosive environment. And as a decorative paint as well.

FEATURES

- Good gloss and color retention
- Excellent spray ability
- Excellent flexibility
- Excellent workability in decorative paint

PHESICAL PROPERTIES

Finish	Matt
Color	Upon Request
Solid by volume	55±5%
Specific Gravity	1.4±0.1 gr/cm ³
Flash point	36 °c
Recommended D.F.T.	40-60 microns
Theoretical coverage	15-8.33 m ² / Lit Practical coverage depends on loss factor
Touch dry	8 hrs. at 20°c
Hard dry	24 hrs. at 20°c
Thermal resistance	Max. 100°c (dry exposure)



kansai paint

Kansai Paint Iranian

Technical Data Sheet: Ref: TDS-HPC-0001-V02

www.kansaipaint.ir

Date of issue: June 2017

APPLICATION

Application method	Air/Airless spray, Brush ,Roller
Surface temperature	10-40 °c
Mixing ratio	Single pack
Packaging	25kg
Thinner/Cleaner	A840-0322
Recoat interval	Min 24 hrs. at 20°c Max 30 days at 20°c Recoating intervals related to later conditions of exposure
Pot Life	N/A
Application condition	Apply only on a dry and clean surface with a temperature above the dew point to avoid condensation Environment Temperature should be 10 °C min and 40 °C max and Relative humidity: 80% maximum.
Nozzle orifice	0.019"-0.021"
Nozzle pressure	150 bar/2175 psi Airless spray is indicative and subject to adjustment

SURFACE PREPRATION

For new steel abrasive blasting to minimum Sa2, alternatively power tool cleaning to St-3. For maintenance remove oil and grease and any other contaminants by suitable detergent and consequently by high-pressure fresh water cleaning .Remove all rust and loose material by abrasive blasting or power-tool cleaning, dust off residues before painting.

SAFETY PRECAUTIONS

Detail information is given on Material Safety Data Sheet (MSDS). Avoid inhalation of spray mist or vapor. Avoid skin and eye contact. Paint contacted with skin should be immediately removed with water and/or suitable cleanser. Eyes should be flushed with water and seek immediate medical attention. Since this product contains flammable solvents, keep away from sparks and open flames. Application and handling of this product should be in compliance with relevant national regulations.

STORAGE

Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept tightly closed. Store conditions shall be in accordance with national regulations.

SHELF LIFE

12 months from date of production.

DISCLAIMER: The information given on this sheet is to the best of our knowledge and accurate at the time of issuing. Since conditions of use are beyond the manufacturer's control information contained herein is without warranty implied or otherwise and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development.