



kansai paint

Kansai Paint Iranian

Technical Data Sheet: Ref: TDS-HPC-0001-V02

Date of issue: June 2017

[www.kansaipaint.ir](http://www.kansaipaint.ir)

## A142-3002

### ACRYLIC INHIBITIVE PAINT

<b>GENERIC TYPE</b>	Acrylic																						
<b>DESCRIPTION</b>	A142-3002 is a quick drying paint based on thermoplastic acrylic resin.																						
<b>RECOMMENDED USE</b>	For use on metal surfaces where a hard, fast dry and adherent and inhibitive coat is required.																						
<b>FEATURE</b>	<ul style="list-style-type: none"><li>-Water resistance</li><li>-Excellent spray ability</li><li>-Excellent flexibility</li><li>-High adhesion to different metallic surfaces</li><li>-Good resistance to different environmental conditions</li></ul>																						
<b>PHYSICAL PROPERTIES</b>	<table><tr><td>Finish</td><td>Semi-Flat, Semi-Gloss</td></tr><tr><td>Color</td><td>Upon request</td></tr><tr><td>Solid by volume</td><td>55±5%</td></tr><tr><td>Specific Gravity</td><td>1.3±0.1 gr/cm<sup>3</sup></td></tr><tr><td>Flash point</td><td>32 °c</td></tr><tr><td>Recommended D.F.T.</td><td>60-80 microns</td></tr><tr><td>Theoretical coverage</td><td>10-6.25 m<sup>2</sup> /Lit</td></tr><tr><td></td><td>Practical coverage depends on loss factor</td></tr><tr><td>Touch dry</td><td>20 min. at 20°c</td></tr><tr><td>Hard dry</td><td>12 hrs. at 20°c</td></tr><tr><td>Thermal resistance</td><td>Max. 120°c (dry exposure)</td></tr></table>	Finish	Semi-Flat, Semi-Gloss	Color	Upon request	Solid by volume	55±5%	Specific Gravity	1.3±0.1 gr/cm <sup>3</sup>	Flash point	32 °c	Recommended D.F.T.	60-80 microns	Theoretical coverage	10-6.25 m <sup>2</sup> /Lit		Practical coverage depends on loss factor	Touch dry	20 min. at 20°c	Hard dry	12 hrs. at 20°c	Thermal resistance	Max. 120°c (dry exposure)
Finish	Semi-Flat, Semi-Gloss																						
Color	Upon request																						
Solid by volume	55±5%																						
Specific Gravity	1.3±0.1 gr/cm <sup>3</sup>																						
Flash point	32 °c																						
Recommended D.F.T.	60-80 microns																						
Theoretical coverage	10-6.25 m <sup>2</sup> /Lit																						
	Practical coverage depends on loss factor																						
Touch dry	20 min. at 20°c																						
Hard dry	12 hrs. at 20°c																						
Thermal resistance	Max. 120°c (dry exposure)																						



kansai paint

Kansai Paint Iranian

Technical Data Sheet: Ref: TDS-HPC-0001-V02

Date of issue: June 2017

[www.kansaipaint.ir](http://www.kansaipaint.ir)

## APPLICATION

Application method	Air/Airless spray, Brush, Roller
Surface temperature	10-50 °c
Mixing ratio	Single pack
Packaging	20 KG
Thinner/cleaner	A840-0142
Pot Life	N/A
Recoat interval	Min 1 hrs. at 20°c Max indefinite Recoating intervals related to later conditions of exposure
Nozzle orifice	0.018"-0.021"
Nozzle pressure	150 bar/2175 psi Airless spray is indicative and subject to adjustment
Application condition	Apply only on a dry and clean surface with a temperature above the dew point to avoid condensation. In confined spaces provide adequate ventilation during application and drying.

## SURFACE PREPARATION

The surface must be clean and dry. Any contamination such as dirt, grease, oil, salt and any other foreign materials should be removed.

## SAFETY PRECAUTIONS

Detail information is given on Material Safety Data Sheet (MSDS). Avoid inhalation of spray mist or vapor. Avoid skin and eye contact. Paint contacted with skin should be immediately removed with water and/or suitable cleanser. Eyes should be flushed with water and seek immediate medical attention. Since this product contains flammable solvents, keep away from sparks and open flames. Application and handling of this product should be in compliance with relevant national regulations.

## STORAGE

Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept tightly closed. Store conditions shall be in accordance with national regulations.

## SHELF LIFE

12 months from date of production

**DISCLAIMER:** The information given on this sheet is to the best of our knowledge and accurate at the time of issuing. Since conditions of use are beyond the manufacturer's control information contained herein is without warranty implied or otherwise and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development.