



kansai paint

Kansai Paint Iranian

Technical Data Sheet: Ref: TDS-HPC-0001-V02

Date of issue: June 2017

[www.kansaipaint.ir](http://www.kansaipaint.ir)

## A142-3004

### TP ACRYLIC COLD TRAFFIC MARKING PAINT (1 PACK)

<b>GENERIC TYPE</b>	Acrylic																		
<b>DESCRIPTION</b>	A142-3004 is a quick drying traffic paint based on thermoplastic acrylic resin with excellent abrasion and weathering resistance.																		
<b>RECOMMENDED USE</b>	<ul style="list-style-type: none"><li>-Suitable for use on concrete and asphalt, especially for road marking both in cities and high-ways.</li><li>-Easy to apply by line striper, brush or roller Keeps lines crisp.</li><li>-Vehicle and pedestrian traffic can resume quickly Stripes remain clean.</li></ul>																		
<b>FEATURE</b>	<ul style="list-style-type: none"><li>-High adhesion to concrete and asphalt</li><li>-Excellent abrasion resistance</li><li>-Excellent water and alkali resistance</li><li>-Excellent whiteness with fluorescent shine</li></ul>																		
<b>PHYSICAL PROPERTIES</b>	<table><tr><td>Finish</td><td>Egg shell</td></tr><tr><td>Color</td><td>White, Yellow ,Black ,Red</td></tr><tr><td>Solid by volume</td><td>52±5%</td></tr><tr><td>Specific Gravity</td><td>1.5±0.1 gr/cm3</td></tr><tr><td>Flash point</td><td>28 °c</td></tr><tr><td>Recommended D.F.T.</td><td>200-400 microns</td></tr><tr><td>Theoretical coverage</td><td>2.85-1.17 m2 /Lit</td></tr><tr><td>Touch dry</td><td>15 min. at 20°C</td></tr><tr><td>Hard dry</td><td>1 hrs. at 20°C</td></tr></table>	Finish	Egg shell	Color	White, Yellow ,Black ,Red	Solid by volume	52±5%	Specific Gravity	1.5±0.1 gr/cm3	Flash point	28 °c	Recommended D.F.T.	200-400 microns	Theoretical coverage	2.85-1.17 m2 /Lit	Touch dry	15 min. at 20°C	Hard dry	1 hrs. at 20°C
Finish	Egg shell																		
Color	White, Yellow ,Black ,Red																		
Solid by volume	52±5%																		
Specific Gravity	1.5±0.1 gr/cm3																		
Flash point	28 °c																		
Recommended D.F.T.	200-400 microns																		
Theoretical coverage	2.85-1.17 m2 /Lit																		
Touch dry	15 min. at 20°C																		
Hard dry	1 hrs. at 20°C																		



kansai paint

Kansai Paint Iranian

Technical Data Sheet: Ref: TDS-HPC-0001-V02

Date of issue: June 2017

[www.kansaipaint.ir](http://www.kansaipaint.ir)

## APPLICATION

Application method Automatic spray, Brush, Roller

Surface temperature 10-45 °c  
Mixing ratio Single pack  
Packaging 25 KG  
Thinner/cleaner Don't Need  
Pot Life N/A  
Recoat interval Indefinite

Application condition Apply only on a dry and clean surface with a temperature above the dew point to avoid condensation. In confined spaces provide adequate ventilation during application and drying. Related Humidity is <80%

## APPLICATION PROCEDURE

Care should be taken to ensure that the surface is clean, dry and free of loose material. A simple leaf blower is typically sufficient to remove gravel and dust in most instances. When applying over previously coated areas however, take special care to remove any loose or peeling paint. Other surface conditions, such as areas with large amounts of Engine oil buildup or existing epoxy coatings, may require a power-washing procedure or abrading the surface before application of the paint. New concrete and asphalt should be aged for a minimum of 30 days prior to painting. For more information on the surface, please consult with the supplier or applicator of the surface.

## SAFETY PRECAUTIONS

Detail information is given on Material Safety Data Sheet (MSDS). Avoid inhalation of spray mist or vapor. Avoid skin and eye contact. Paint contacted with skin should be immediately removed with water and/or suitable cleanser. Eyes should be flushed with water and seek immediate medical attention. Since this product contains flammable solvents, keep away from sparks and open flames. Application and handling of this product should be in compliance with relevant national regulations.

## STORAGE

Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept tightly closed. Store conditions shall be in accordance with national regulations.

## GENERAL REMARKS

Mix well before using. Keep tightly covered to prevent skinning.

-Contractor can add glass traffic beads.

-Surfaces must be clean and dry, at a minimum of 5 Degree of Centigrade.

-Good application to asphalt, concrete, and brick masonry Minimizes bleeding upon application

## SURFACE PREPRATION

-Surface must be thoroughly dry and free from dust, rust, grease, oil, loose particles or earlier coating.

-Carry out all repair work like joint sealing, filling of cracks, cavities and crevices with appropriate Materials.

## SHELF LIFE

6 months from date of production

**DISCLAIMER:** The information given on this sheet is to the best of our knowledge and accurate at the time of issuing. Since conditions of use are beyond the manufacturer's control information contained herein is without warranty implied or otherwise and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development.